

In the Claims

1. (Currently amended.) A lithium ion secondary battery comprising a positive electrode, a negative electrode and a solid electrolyte, said solid electrolyte being made in the form of a thin film comprising a lithium ion conductive inorganic substance, selected from the group consisting of a lithium ion conductive crystal and a lithium ion conductive glass-ceramic, said thin film solid electrolyte having a thickness of 20  $\mu\text{m}$  or below.
2. (Cancelled.)
- 3 ( Original.) A lithium ion secondary battery as defined in claim 1 wherein said thin film solid electrolyte is formed directly on an electrode material or materials for the positive electrode and/or the negative electrode.
4. (Original.) A lithium ion secondary battery as defined in claim 1 wherein said thin film solid electrolyte has lithium ion conductivity of  $10^{-5} \text{ Scm}^{-1}$  or over.
5. (Original.) A lithium ion secondary battery as defined in claim 1 wherein said thin film solid electrolyte comprises the inorganic substance in an amount of 40 weight % or over.
6. (Previously presented) A lithium ion secondary battery as defined in claim 1 wherein said inorganic substance is a lithium ion conductive crystal.
7. (Cancelled.)
8. (Previously presented.) A lithium ion secondary battery as defined in claim 1 wherein said inorganic substance is a lithium ion conductive glass-ceramic.
9. (Original.) A lithium ion secondary battery as defined in claim 1 wherein said inorganic substance is powder of the inorganic substance.

10. (Previously presented.) A lithium ion secondary battery as defined in claim 9 wherein said inorganic substance powder is powder of a lithium ion conductive glass-ceramic.
11. (Original.) A lithium ion secondary battery as defined in claim 9 wherein an average particle diameter of the inorganic substance powder is 1.0  $\mu\text{m}$  or below.
12. (Original.) A lithium ion secondary battery as defined in claim 9 wherein said thin film solid electrolyte comprises a lithium ion conductive inorganic substance powder in a polymer medium.
13. (Original.) A lithium ion secondary battery as defined in claim 9 wherein said thin film solid electrolyte comprises a lithium inorganic salt and lithium ion conductive glass-ceramic powder in a polymer medium.
14. (Original.) A lithium ion secondary battery as defined in claim 3 wherein said thin film solid electrolyte is formed by direct coating on an electrode material or materials for the positive electrode and/or the negative electrode.
15. (Original.) A lithium ion secondary battery as defined in claim 3 wherein said thin film solid electrolyte is formed by crystallizing an amorphous layer which is formed by direct coating on an electrode material or materials for the positive electrode and/or the negative electrode.
16. (Original.) A lithium ion secondary battery as defined in claim 1 comprising a positive electrode, a negative electrode and a solid electrolyte wherein said positive and/or negative electrode comprises lithium ion conductive inorganic substance powder.
17. (Original.) A lithium ion secondary battery as defined in claim 16 wherein said inorganic substance powder in the positive and/or negative electrode has an average particle diameter of 3  $\mu\text{m}$  or below.

18. (Cancelled.)

19. (Cancelled.)

20. (Cancelled.)

18. (Cancelled.)

19. (Cancelled.)

20. (Cancelled.)